

CHRYSO® Delta G533

New Generation Admixture for Concrete



Description

CHRYSO® Delta G533 is a new generation multi range Admixture based on expertise hybrid Poly Carboxylate polymers technology. To provide,

- A wide scale of dosage.
- A moderate water reduction at low dosage while higher water reduction can be achieved with increase in dosage.
- Better flow with low Thixotropy & good retention.

Indicative characteristics

- Form : Light Amber Liquid
- Specific Gravity : 1.03 ± 0.02
- Air entrainment : $\leq 1.5\%$ over control mix.
- pH : ≥ 6
- Chloride Content : Nil, as per BS - 5075 (Part-I)
- Compatibility : OPC, Fly Ash, GGBS, PPC, and SRC.

ADVANTAGES :

Thanks to specifically designed molecular structure, CHRYSO® Delta G533 has a great flexibility; thanks to its large scale of dosage, it can be used in wide range of concrete with desired fluidity & workability retention. At equal plasticity, and after reducing mixing water:

- Concrete compacity is improved.
- Capillary absorption is reduced.

Depending on dosage, a relative increase of mechanical strength is observed at 24 hours & is a great advantage too over Old generation Admixtures available in the market. For any mix, keeping the cement consumption and workability constant, substantial reduction in the amount of mixing water can be achieved, to produce concrete of high compressive strength.

This also enables the concrete manufacturer to produce cohesive, free concrete with desired workability retention along with our slump retainer, "CHRYSO® Tard SRC/ CHRYSO® Tard SRC80" which helps manufacturer to place & pump concrete easily in vertical as well as horizontal direction & still be placed conveniently around congested reinforcement. It reduces thixotropy of the mix without risk of segregation. It is well compatible with GGBS, Fly Ash like supplementary materials.

Domains of application

- All cement types.
- Fluid, Pumpable with desired retention Concrete production.
- Especially for job site/ Ready Mix Concrete production.
- GGBS/Fly Ash content concrete mix.
- Suitable for various grades of concrete.

Precautions

Not to be stored at high temperatures for long periods. Should be protected from frost. It is Non-toxic and formulated from chemicals which present no fire or health hazards.

Method of use

Dosage: Optimum dosage can only be established after trials, taking into account the rheological characteristics and the required mechanical performances. Rate of addition is generally in the range of 0.4% - 2.5 % by wt of cementitious material. For maximum dispersion throughout the mix, CHRYSO® Delta G533 should be added to the mixing water only. Should the product be added to fresh concrete, into the mixing truck, it is necessary to mix at high speed, and then at low speed (with a minimum 3 minutes at each speed)

Guideline Followed :

IS: 9103-2007 and ASTM C-494-2010(Type-F&G).

Shelf Life: If stored in unopened containers at normal ambient temperatures, a shelf-life of approximately 6 months.

Packaging

- 225 Kgs Barrel & bulk in 10 KL tanker

Safety

Before use, refer to the Material Safety Data Sheet. The MSDS is available on www.chryso.com.

The information contained in this technical data sheet is given to the best of our knowledge and the results from extensive testing in order to remain as objective as possible. However, it cannot, in any case be considered as a warranty involving our liability in case of misuse or any different use of our products from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users. Consult the latest update of the technical data sheet on our website www.chryso.com

CHRYSO India Private Limited | Registered & Corporate Office : Plot No. D -30/7, TTC Industrial Area, M.I.D.C. Turbhe, Navi Mumbai – 400705. Maharashtra, INDIA. Tel : +91 22 27685991/2

