

CHRYSO® Optima S662DE

High Range Water Reducing Admixture

DESCRIPTION

CHRYSO® Optima S662 DE is a new generation superplasticizer based on POLYCARBOXYLIC ETHER. It allows concrete to achieve targeted workability, while reducing water / cement ratio. It is developed to maintain fresh concrete workability without compromising setting time. CHRYSO® Optima S662 DE is especially adapted for Ready Mix Concrete and fluid concrete which require short and long term high strengths.

Domains of application

- All cement and cementitious types
- Pumped concrete
- SCC Concrete
- Workability retention
- Ready mix concrete
- Concrete for highly reinforced structures
- High performance concrete

BENEFITS

Thanks to specifically designed molecular structure, CHRYSO® Optima S662 DE enables the concrete manufacturer to produce cohesive, low viscous concrete with long workability retention. Reduces thixotropy of the mix without risk of segregation. High water reduction minimizes shrinkage or cracking yielding better surface finish. For a given concrete mix, keeping the cement consumption and workability constant, substantial reduction in the amount of mixing water can be achieved, to produce concrete of high compressive strength. Alternatively, for the same concrete mix, keeping everything else constant, a definite economy in cement content, can be achieved.

INDICATIVE INFORMATION

Product Nature	liquid
Color	Light Amber
Lifetime	12 months
Cl ⁻ ions content	≤ 0,200 %
Specific gravity	1,095 ± 0,020
pH	7,00 ± 1,00

METHOD OF USE

For maximum dispersion throughout the mix, CHRYSO® Optima S662 DE should be added to the mixing water only. When the product to be added to fresh concrete into the mixing truck, it is necessary to mix at high speed and then at low speed (with a minimum 3 minutes at each speed)

Dosage :

Rate of addition is generally in the range of 0.3-1.5% by weight of Cement and cementitious material.

Implementation :

IS: 9103-2007 and ASTM C-494-1981(Type-G).

PRECAUTIONS

- Protect from heat.
- Protect from humidity.

Not to be stored at high temperatures for long periods. Should be protected from frost. It is Non-toxic and formulated from chemicals which present no fire or health hazards.

SAFETY

Prior to any use, please read carefully the Material Safety Data Sheets.